

CHEMICAL RESISTANCE CHART

	AM015	AM110	AM137M	AM139	AM154	AM321	AM707	NP1	NP010	NP013
ACETIC ACID 5%	B	B	B	A	A	C	C	B	B	B
ACETIC ACID 10%	A	A	A	A	A	B	B	A	A	A
ACETONE	A	B	B	A	B	B	B	C	A	A
AMMONIA	C	C	D	B	C	D	D	D	C	C
BUTANOL	C	C	C	A	C	D	D	D	C	C
ETHYLENE GLYCOL	C	C	D	B	C	D	D	D	C	C
ETHANOL	B	B	C	A	B	D	B	C	B	B
HYDROCHLORIC ACID 10%	B	C	C	C	C	D	C	C	B	B
HYDROCHLORIC ACID 36%	B	A	B	B	B	C	C	B	B	B
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	B	B	A	A	A	A
NITRIC ACID 5%	B	A	B	B	B	D	C	B	B	B
NITRIC ACID 30%	A	A	B	A	A	C	B	B	A	A
PHOSPHORIC ACID 40%	B	B	B	B	A	D	C	B	B	B
SULFURIC ACID 10%	B	B	C	C	C	D	C	C	B	B
SULFURIC ACID 30%	A	A	B	B	B	C	B	B	A	A
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	C	C	E	D	E	E	D	E	C	C
SODIUM HYDROXIDE 50%	B	C	E	D	D	D	C	E	B	B
SKYDROL	B	B	B	A	B	D	C	B	B	B
1,1,1 TRICHLOROETHANE	B	C	B	A	A	C	C	B	B	B
XYLENE	B	B	C	A	B	E	C	C	B	B

A= NOT RECOMMENDED

B= SHORT TERM EXPOSURE/SPLASH SPILL

C= LONG TERM EXPOSURE/SPLASH SPILL

D= SHORT TERM IMMERSION

E= LONG TERM IMMERSION

*= HEAT CURE

This data is provided as a service of National Polymers Inc. and is believed to be accurate. However this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	NP015	NP030	NP70	NP94	NP95	NP100	NP100HV	NP100LVP	NP105	NP110
ACETIC ACID 5%	B	A	B	C	B	C	B	C	B	B
ACETIC ACID 10%	A	A	A	B	A	B	A	B	A	A
ACETONE	A	A	C	B	C	B	C	B	A	B
AMMONIA	C	B	D	C	D	C	D	C	B	C
BUTANOL	C	B	C	D	D	D	D	D	B	C
ETHYLENE GLYCOL	C	B	D	D	D	D	D	D	B	C
ETHANOL	B	A	B	B	C	B	C	B	A	B
HYDROCHLORIC ACID 10%	B	B	C	C	C	C	C	C	B	C
HYDROCHLORIC ACID 36%	B	B	B	C	B	B	B	B	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A	A	A
NITRIC ACID 5%	B	A	B	C	B	C	B	C	B	A
NITRIC ACID 30%	A	A	B	B	B	B	B	B	A	A
PHOSPHORIC ACID 40%	B	B	B	C	B	B	B	C	A	B
SULFURIC ACID 10%	B	B	C	C	C	C	C	C	B	B
SULFURIC ACID 30%	A	A	B	B	B	C	B	B	A	A
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	C	B	E	D	E	C	E	C	C	C
SODIUM HYDROXIDE 50%	B	B	E	C	E	C	E	C	C	C
SKYDROL	B	A	B	C	B	B	B	B	A	B
1,1,1 TRICHLOROETHANE	B	A	B	C	B	C	B	C	A	C
XYLENE	B	A	C	C	C	C	C	C	A	B

A= NOT RECOMMENDED

B= SHORT TERM EXPOSURE/SPLASH SPILL

C= LONG TERM EXPOSURE/SPLASH SPILL

D= SHORT TERM IMMERSION

E= LONG TERM IMMERSION

*= HEAT CURE

This data is provided as a service of National Polymers Inc. and is believed to be accurate. However this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	NP114-2	NP120	NP120SL	NP123	NP124	NP128	NP130	NP131M	NP135M
ACETIC ACID 5%	A	B	B	B	B	B	A	A	B
ACETIC ACID 10%	A	A	A	A	B	A	A	A	A
ACETONE	B	B	B	B	A	B	A	A	C
AMMONIA	C	D	D	C	C	C	C	C	D
BUTANOL	C	D	D	C	C	C	C	C	D
ETHYLENE GLYCOL	C	D	D	C	D	C	C	C	D
ETHANOL	B	B	C	A	C	C	C	C	C
HYDROCHLORIC ACID 10%	A	C	C	C	C	C	C	C	C
HYDROCHLORIC ACID 36%	A	B	B	B	A	A	A	A	B
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A	A
NITRIC ACID 5%	A	B	B	B	B	B	B	B	B
NITRIC ACID 30%	A	B	B	B	A	A	A	A	B
PHOSPHORIC ACID 40%	A	C	C	B	A	A	A	A	B
SULFURIC ACID 10%	A	C	C	C	C	C	B	B	C
SULFURIC ACID 30%	A	C	C	B	A	B	A	A	B
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	C	D	D	C	D	D	D	D	E
SODIUM HYDROXIDE 50%	B	D	D	C	C	D	C	C	E
SKYDROL	A	B	B	B	B	A	A	A	B
1,1,1 TRICHLOROETHANE	B	C	C	C	C	C	C	C	B
XYLENE	B	C	C	C	C	C	C	C	C

A= NOT RECOMMENDED

B= SHORT TERM EXPOSURE/SPLASH SPILL

C= LONG TERM EXPOSURE/SPLASH SPILL

D= SHORT TERM IMMERSION

E= LONG TERM IMMERSION

*= HEAT CURE

This data is provided as a service of National Polymers Inc. and is believed to be accurate. However this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	NP137M	137MUV	NP139	NP144	NP154	NP154VOC	NP162	NP181	NP183	NP210
ACETIC ACID 5%	B	B	A	A	A	A	B	C	D	A
ACETIC ACID 10%	A	A	A	A	A	A	A	B	C	A
ACETONE	C	B	A	B	B	B	B	B	B	A
AMMONIA	D	D	B	C	C	C	C	C	C	D
BUTANOL	C	C	A	C	C	C	C	C	C	C
ETHYLENE GLYCOL	D	D	B	C	C	C	C	D	D	B
ETHANOL	C	C	A	B	B	B	B	B	B	A
HYDROCHLORIC ACID 10%	C	C	C	C	C	C	C	C	D	C
HYDROCHLORIC ACID 36%	B	B	A	B	B	B	A	B	C	A
METHYLENE CHLORIDE	A	A	A	A	A	A	B	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A	A	A
NITRIC ACID 5%	B	B	B	B	B	B	B	C	D	B
NITRIC ACID 30%	B	B	A	A	A	A	A	B	B	A
PHOSPHORIC ACID 40%	B	B	B	A	A	A	B	C	D	A
SULFURIC ACID 10%	C	C	C	C	C	C	B	D	D	B
SULFURIC ACID 30%	B	B	A	B	B	B	A	C	D	A
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	E	E	D	E	E	E	D	E	E	E
SODIUM HYDROXIDE 50%	E	E	D	D	D	D	C	E	E	C
SKYDROL	B	B	A	B	B	B	B	C	C	B
1,1,1 TRICHLOROETHANE	B	B	A	A	A	A	C	B	B	B
XYLENE	C	C	A	B	B	B	B	B	B	C

A= NOT RECOMMENDED

B= SHORT TERM EXPOSURE/SPLASH SPILL

C= LONG TERM EXPOSURE/SPLASH SPILL

D= SHORT TERM IMMERSION

E= LONG TERM IMMERSION

*= HEAT CURE

This data is provided as a service of National Polymers Inc. and is believed to be accurate. However this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	NP220	NP320/321	NP322	NP341	356PAVOC	NP357VOC	NP357	NP358	NP380	NP707
ACETIC ACID 5%	A	C	B	C	C	C	C	C	C	C
ACETIC ACID 10%	B	B	B	B	B	B	B	B	B	B
ACETONE	B	B	B	B	B	B	B	B	B	C
AMMONIA	C	D	D	D	D	D	D	D	C	C
BUTANOL	C	D	D	D	D	D	D	D	C	D
ETHYLENE GLYCOL	C	D	D	D	D	D	D	D	D	D
ETHANOL	C	D	C	B	D	D	D	D	B	B
HYDROCHLORIC ACID 10%	C	D	C	C	D	D	D	D	C	C
HYDROCHLORIC ACID 36%	B	C	B	C	C	C	C	C	B	B
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	B	A	A	B	B	B	B	A	A
NITRIC ACID 5%	C	D	C	D	D	D	D	D	C	C
NITRIC ACID 30%	B	C	B	C	C	C	C	B	B	B
PHOSPHORIC ACID 40%	B	D	C	D	D	D	D	D	C	B
SULFURIC ACID 10%	C	D	D	C	D	D	D	D	D	C
SULFURIC ACID 30%	B	C	C	C	C	C	C	C	B	C
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	E	E	E	E	E	E	E	E	E	C
SODIUM HYDROXIDE 50%	C	D	D	E	D	D	D	D	E	C
SKYDROL	B	D	C	C	D	D	D	D	C	B
1,1,1 TRICHLOROETHANE	B	C	C	B	C	C	C	C	B	C
XYLENE	B	D	B	C	D	E	D	D	B	C

A= NOT RECOMMENDED

B= SHORT TERM EXPOSURE/SPLASH SPILL

C= LONG TERM EXPOSURE/SPLASH SPILL

D= SHORT TERM IMMERSION

E= LONG TERM IMMERSION

*= HEAT CURE

This data is provided as a service of National Polymers Inc. and is believed to be accurate. However this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	NP707WF	NP818	NP820	NP821	NP829	NP829HV	NP831	NP7175
ACETIC ACID 5%	B	B	A	A	B	B	B	B
ACETIC ACID 10%	A	A	A	A	A	A	A	A
ACETONE	B	A	B	B	A	A	A	B
AMMONIA	C	B	C	C	C	C	TD	C
BUTANOL	C	C	C	C	C	C	C	C
ETHYLENE GLYCOL	C	C	C	C	D	D	D	C
ETHANOL	B	A	B	A	C	C	C	B
HYDROCHLORIC ACID 10%	C	B	C	C	B	B	TC	B
HYDROCHLORIC ACID 36%	A	A	B	A	A	A	TB	B
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A
NITRIC ACID 5%	B	B	B	B	B	B	B	B
NITRIC ACID 30%	A	A	A	A	A	A	B	A
PHOSPHORIC ACID 40%	A	A	A	A	A	A	TB	B
SULFURIC ACID 10%	C	B	C	C	B	B	B	B
SULFURIC ACID 30%	B	A	B	B	A	A	TB	A
SULFURIC ACID 98%	TC	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	E	D	E	E	D	D	D	C
SODIUM HYDROXIDE 50%	D	C	D	D	D	D	D	B
SKYDROL	B	A	B	B	B	B	B	B
1,1,1 TRICHLOROETHANE	C	A	A	B	B	B	B	A
XYLENE	B	B	B	B	B	B	TC	B

A= NOT RECOMMENDED

B= SHORT TERM EXPOSURE/SPLASH SPILL

C= LONG TERM EXPOSURE/SPLASH SPILL

D= SHORT TERM IMMERSION

E= LONG TERM IMMERSION

*= HEAT CURE

This data is provided as a service of National Polymers Inc. and is believed to be accurate. However this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.