

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
ACETALDEHYDE	D	C	B	D	D	D	D	TD	C	C	C
ACETIC ACID 5%	D	D	B	D	D	D	D	D	D	D	D
ACETIC ACID 10%	B	B	A	C	C	B	B	B	C	C	C
ACETIC ACID 25%	B	B	A	C	C	B	B	B	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	D	C	B	D	D	D	D	D	C	C	C
ACETONE 10%	C	C	B	D	D	C	C	C	C	C	C
ACETONE 100%	C	C	B	C	C	C	C	C	C	C	C
ACETYL CHLORIDE	TC	TC	TB	TD	TD	TC	TC	TC	TB	TB	TB
ACETONITRILE	D	C	B	D	D	D	D	D	C	C	C
ACRYLIC ACID	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
ACRYLONITRILE	TB	TB	A	TB	TB	TB	TB	TB	TB	TB	TB
ADIPIC ACID 25%	C	C	B	C	C	C	C	C	B	B	B
ALLYL ALCOHOL	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
ALLYL CHLORIDE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
ALUMINUM BROMIDE	D	D	C	E	E	D	D	D	D	D	D
ALUMINUM CHLORIDE	TD	TD	TC	TE	TE	TD	TD	TD	TD	TD	TD
ALUMINUM FLUORIDE	TD	TD	TC	TE	TE	TD	TD	TD	TD	TD	TD
ALUMINUM HYDROXIDE	D	D	C	E	E	D	D	D	D	D	D
ALUMINUM NITRATE	E	D	C	E	E	E	E	E	D	D	D
ALUMINUM SULFATE	D	D	C	E	E	D	D	D	D	D	D
AMMONIA	E	D	C	E	E	E	E	E	D	D	D
AMMONIUM CHLORIDE	TD	TD	TC	TD	TD	TD	TD	TD	TD	TD	TD
AMMONIUM FLUORIDE	TC	TC	TB	TC	TC	TC	TC	TC	TC	TC	TC

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>AMMONIUM HYDROXIDE</b>	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
<b>AMMONIUM NITRATE</b>	E	E	D	E	E	E	E	E	D	D	D
<b>AMMONIUM OXALATE</b>	D	D	TC	D	D	D	D	D	C	C	C
<b>AMMONIUM NITRATE AMMONIUM PERSULFATE</b>	TE	TD	TC	TE	TE	TE	TE	TE	TD	TD	TD
<b>AMMONIUM PERSULFATE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>AMMONIUM PHOSPHATE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>AMMONIUM SULFATE</b>	D	D	C	E	E	D	D	D	C	C	C
<b>AMMONIUM SULFIDE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>AMMONIUM SULFITE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>AMYL ACETATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>AMYL ALCOHOL</b>	D	C	B	D	D	D	D	D	C	C	C
<b>ANILINE</b>	C	B	A	D	D	C	C	C	B	B	B
<b>ANILINE HYDROCHLORIDE</b>	C	B	A	D	D	C	C	C	B	B	B
<b>ANTIMONY CHLORIDE</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>AQUA REGIA</b>	A	A	A	A	A	A	A	A	A	A	A
<b>ARSENOUS ACID</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>BARIUM ACETATE</b>	D	C	B	E	E	D	D	D	D	D	D
<b>BARIUM BROMIDE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>BARIUM CARBONATE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>BARIUM CHLORIDE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>BARIUM HYDROXIDE</b>	TD	TC	TB	TE	TE	TD	TD	TD	TD	TD	TD
<b>BARIUM SULFATE</b>	D	C	B	E	E	D	D	D	D	D	D
<b>BARIUM SULFIDE</b>	C	C	B	D	D	C	C	C	C	C	C
<b>BENZYL CHLORIDE</b>	TC	TC	A	TD	TD	TC	TC	TC	TC	TC	TC

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>BENZOIC ACID</b>	C	C	B	D	D	C	C	C	C	C	C
<b>BENZALDEHYDE</b>	TC	TC	TB	TC	TC	TC	TC	TC	TC	TC	TC
<b>BENZENE</b>	TC	TC	TB	TD	TD	TC	TC	TC	TC	TC	TC
<b>BENZYL ALCOHOL</b>	E	D	C	E	E	E	E	E	D	D	D
<b>BLACK LIQUOR (PAPER)</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>BLOOD SUGAR</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>BORAX</b>	D	C	B	D	D	D	D	D	C	C	C
<b>BORIC ACID</b>	C	C	B	D	D	C	C	C	C	C	C
<b>BRINE</b>	E	D	D	E	E	E	E	E	D	D	D
<b>BROMINE LIQUID</b>	A	A	A	A	A	A	A	A	A	A	A
<b>BUTANOL</b>	E	D	C	E	E	E	E	E	D	D	D
<b>BUTYL ACETATE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>BUTYL ACRYLATE</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>BUTYL AMINE</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>BUTYL CARBITOL</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>BUTYL CELLOSOLVE</b>	C	C	B	D	D	C	C	C	C	C	C
<b>BUTYL ETHER</b>	D	C	B	D	D	D	D	D	C	C	C
<b>BUTYRIC ACID</b>	B	B	A	C	C	B	B	B	B	B	B
<b>CALCIUM BISULFITE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>CALCIUM BROMIDE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>CALCIUM CARBONATE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>CALCIUM CHLORATE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>CALCIUM CHLORIDE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>CALCIUM HYDROXIDE</b>	E	D	B	E	E	E	E	E	C	C	C

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>CALCIUM HYPOCHLORITE</b>	TC	TC	TB	TD	TD	TC	TC	TC	TC	TC	TC
<b>CALCIUM NITRATE</b>	E	E	D	E	E	E	E	E	D	D	D
<b>CALCIUM SULFATE</b>	C	C	B	D	D	C	C	C	C	C	C
<b>CALCIUM SULFITE</b>	C	C	B	D	D	C	C	C	C	C	C
<b>CALCIUM DISULFIDE</b>	B	B	A	C	C	B	B	B	C	C	C
<b>CARBON TETRACHLORIDE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>CASTOR OIL</b>	D	C	B	E	E	D	D	D	C	C	C
<b>CELLOSOLVE</b>	TD	TD	TC	TD	TD	TD	TD	TD	TD	TD	TD
<b>CELLOSOLVE ACETATE</b>	C	C	B	D	D	C	C	C	C	C	C
<b>CHLOROACETIC ACID 25%</b>	C	C	A	C	C	C	C	C	A	A	A
<b>CHLOROACETIC ACID 50%</b>	A	A	A	A	A	A	A	A	A	A	A
<b>CHLOROBENZENE</b>	D	C	B	D	D	D	D	D	B	B	B
<b>CHLOROFORM</b>	TC	TB	A	TC	TC	TC	TC	TC	A	A	A
<b>CHLOROPHENOL</b>	A	A	A	A	A	A	A	A	A	A	A
<b>CHLOROSULFONIC ACID</b>	A	A	A	A	A	A	A	A	A	A	A
<b>CHLOROTOLUENE</b>	TC	TC	A	TD	TD	TC	TC	TC	TB	TB	TB
<b>CHROMIC ACID 10%</b>	B	B	A	C	C	C	C	B	B	B	B
<b>CHROMIC ACID 40%</b>	B	B	A	B	B	B	B	B	A	A	A
<b>CHROMIC CHLORIDE</b>	B	B	A	B	B	B	B	B	A	A	A
<b>CITRIC ACID</b>	E	D	B	E	E	E	E	E	D	D	D
<b>COPPER ACETATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>COPPER CHLORIDE</b>	D	C	B	D	D	D	D	D	D	D	D
<b>COPPER CYANIDE</b>	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
<b>COPPER NITRATE</b>	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>COPPER SULFATE</b>	D	C	B	D	D	D	D	D	B	B	B
<b>CORN OIL</b>	D	C	B	E	E	D	D	D	C	C	C
<b>CORN STARCH SLURRY</b>	E	E	E	E	E	E	E	E	E	E	E
<b>CORN SUGAR</b>	E	D	C	E	E	E	E	E	C	C	C
<b>COTTONSEED OIL</b>	D	C	B	E	E	D	D	D	C	C	C
<b>CREOSOTE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>CRESYLIC ACID</b>	TC	TB	A	TD	TD	TC	TC	TC	TB	TB	TB
<b>CUMENE</b>	D	C	B	E	E	D	D	D	B	B	B
<b>CUTTING OIL</b>	D	C	B	E	E	D	D	D	C	C	C
<b>CYCLOHEXANE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>CYCLOHEXANONE</b>	D	D	C	E	E	E	E	D	C	C	C
<b>CYMENE</b>	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
<b>DETERGENTS ORGANIC</b>	TD	TD	TC	TE	TE	TD	TD	TD	TC	TC	TC
<b>DETERGENTS SULFONATED</b>	TD	TD	TC	TE	TE	TD	TD	TD	TC	TC	TC
<b>DEXTROSE</b>	E	E	E	E	E	E	E	E	E	E	E
<b>DIBUTYL PHTHALATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>DICHLORACETIC ACID</b>	TB	TB	TB	TC	TC	TB	TB	TB	TB	TB	TB
<b>DICHLOROBENZENE</b>	D	C	B	E	E	D	D	D	C	C	C
<b>DICHLOROETHANE</b>	C	B	A	C	C	C	C	C	A	A	A
<b>DIESEL FUEL</b>	D	C	B	D	D	D	D	D	B	B	B
<b>DIETHANOLAMINE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>DIETHYL BENZENE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>DIETHYL KETONE</b>	TD	TC	A	TD	TD	TD	TD	TD	TB	TB	TB
<b>DIETHYLENE GLYCOL</b>	E	D	B	E	E	E	E	E	C	C	C

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>DIETHYL ETHER</b>	D	C	B	D	D	D	D	D	C	C	C
<b>DIMETHYL ANILINE</b>	TC	TB	A	TD	TD	TC	TC	TC	TB	TB	TB
<b>DIMETHYL FORMAMIDE</b>	A	A	A	A	A	A	A	A	A	A	A
<b>DIMETHYL SULFOXIDE</b>	B	B	A	B	B	B	B	B	A	A	A
<b>DINITRO BENZENE</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>DINITRO TOLUENE</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>EPOCHLOROHYDRIN</b>	C	B	A	D	D	C	C	C	B	B	B
<b>ETHANOL</b>	C	C	B	C	C	C	C	C	C	C	C
<b>ETHANOLAMINE</b>	D	C	A	D	D	D	D	D	B	B	B
<b>ETHYL ACETATE</b>	C	B	A	C	C	C	C	C	B	B	B
<b>ETHYL ACRYLATE</b>	C	C	A	C	C	C	C	C	B	B	B
<b>ETHYLAMINE</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>ETHYL BENZENE</b>	TD	TC	A	TD	TD	TD	TD	TD	TB	TB	TB
<b>ETHYL BROMIDE</b>	B	B	A	B	B	B	B	B	A	A	A
<b>ETHYL CHLORIDE</b>	B	B	A	B	B	B	B	B	A	A	A
<b>ETHYL DICHLORIDE</b>	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
<b>ETHYLENE GLYCOL</b>	E	D	C	E	E	E	E	E	D	D	D
<b>ETHYL SULFATE</b>	TD	TC	A	TD	TD	TD	TD	TD	TC	TC	TC
<b>FATTY ACIDS</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>FERRIC CHLORIDE</b>	E	E	D	E	E	E	E	E	D	D	D
<b>FERRIC SULFATE</b>	E	E	D	E	E	E	E	E	D	D	D
<b>FERROUS NITRATE</b>	E	E	B	E	E	E	E	E	C	C	C
<b>FERROUS CHLORIDE</b>	TD	TD	TC	TD	TD	TD	TD	TD	TD	TD	TD
<b>FERROUS SULFATE</b>	TE	TD	TD	TE	TE	TE	TE	TE	TD	TD	TD

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>FLUOSILICIC ACID 10-25%</b>	A	A	A	A	A	A	A	A	A	A	A
<b>FORMALDEHYDE</b>	D	C	B	E	E	D	D	D	B	B	B
<b>FORMIC ACID 10%</b>	D	C	A	D	D	D	D	D	B	B	B
<b>FORMIC ACID 50%</b>	B	C	A	B	B	B	B	B	A	A	A
<b>FUEL OIL</b>	E	D	B	E	E	E	E	E	B	B	B
<b>FURFURAL ALCOHOL</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>GASOLINE AVIATION</b>	D	D	C	D	D	D	D	D	C	C	C
<b>GASOLINE DIESEL</b>	D	D	C	D	D	D	D	D	C	C	C
<b>GASOLINE JET FUEL</b>	D	D	C	D	D	D	D	D	C	C	C
<b>GASOLINE UNLEADED</b>	E	D	C	E	E	E	E	E	C	C	C
<b>GLUCOSE</b>	E	E	D	E	E	E	E	E	D	D	D
<b>GLYCERINE</b>	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
<b>GLYCOLIC ACID 70%</b>	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
<b>GREEN LIQUOR (PAPER)</b>	E	D	B	E	E	E	E	E	C	C	C
<b>HEPTANE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>HEXANE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>HYDRAULIC FLUID</b>	E	D	B	E	E	E	E	E	C	C	C
<b>HYDRAZINE 35%</b>	TC	TB	A	TC	TC	TC	TC	TC	A	A	A
<b>HYDRIODIC ACID 20%</b>	D	C	A	D	D	D	D	D	B	B	B
<b>HYDROBROMIC ACID 18%</b>	C	B	A	C	C	C	C	C	B	B	B
<b>HYDROBROMIC ACID 40%</b>	TB	TB	A	TC	TC	TB	TB	TB	A	A	A
<b>HYDROBROMIC ACID 60%</b>	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
<b>HYDROCHLORIC ACID 10%</b>	D	D	C	D	D	D	D	D	D	D	D
<b>HYDROCHLORIC ACID 36%</b>	D	C	B	D	D	D	D	D	C	C	C

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>HYDROFLUORIC ACID</b>	A	A	A	A	A	A	A	A	A	A	A
<b>HYDROGEN PEROXIDE 10%</b>	C	B	A	C	C	C	C	C	B	B	B
<b>HYDROGEN PEROXIDE 50%</b>	A	A	A	A	A	A	A	A	A	A	A
<b>HYDROGEN SULFIDE 5%</b>	D	C	B	D	D	D	D	D	C	C	C
<b>HYDROGEN SULFIDE 100%</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>HYPOCHLOROUS ACID</b>	A	A	A	A	A	A	A	A	A	A	A
<b>IODINE CRYSTALS/VAPOR</b>	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
<b>ISOPHORONE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>ISOPROPYL ACETATE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>ISOPROPYL ALCOHOL</b>	E	D	B	E	E	E	E	E	C	C	C
<b>JET FUEL (JP-4)</b>	D	D	C	D	D	D	D	D	C	C	C
<b>KEROSENE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>LACTIC ACID 10-20%</b>	D	D	D	D	D	D	D	D	C	C	C
<b>LACTIC ACID 50%</b>	C	B	A	C	C	C	C	C	A	A	A
<b>LACTIC ACID 85%</b>	A	A	A	A	A	A	A	A	A	A	A
<b>LAURIC ACID</b>	TD	TC	A	TD	TD	TD	TD	TD	TB	TB	TB
<b>LEAD ACETATE</b>	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
<b>LEVULINIC ACID</b>	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
<b>LINSEED OIL</b>	D	C	B	D	D	D	D	D	C	C	C
<b>LITHIUM BROMIDE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>LITHIUM CHLORIDE SAT'D</b>	D	C	B	D	D	D	D	D	B	B	B
<b>LITHIUM HYDROXIDE</b>	TC	TB	A	TD	TD	TC	TC	TC	TB	TB	TB
<b>MAGNESIUM BISULFITE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>MAGNESIUM CARBONATE</b>	D	D	C	D	D	D	D	D	C	C	C

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>MAGNESIUM CHLORIDE</b>	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
<b>MAGNESIUM HYDROXIDE</b>	C	C	B	C	C	C	C	C	B	B	B
<b>MAGNESIUM NITRATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>MAGNESIUM SULFATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>MALEIC ACID</b>	C	B	A	C	C	C	C	C	B	B	B
<b>MANGANESE CHLORIDE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>MANGANESE SULFATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>MERCURIC CHLORIDE</b>	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
<b>MERCUROUS CHLORIDE</b>	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
<b>METHANOL</b>	C	B	B	C	C	C	C	C	B	B	B
<b>METHYL ACETATE</b>	C	B	A	C	C	C	C	C	B	B	B
<b>METHYLAMYL ALCOHOL</b>	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
<b>METHYL BENZOATE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>METHYL CHLORIDE</b>	B	B	A	B	B	B	B	B	A	A	A
<b>METHYLENE CHLORIDE</b>	A	A	A	A	A	A	A	A	A	A	A
<b>METHYL ETHYL KETONE</b>	C	B	A	C	C	C	C	C	A	A	A
<b>METHYL ISOBUTYL KETONE</b>	D	C	B	D	D	D	D	D	B	B	B
<b>MILK</b>	E	E	D	E	E	E	E	E	D	D	D
<b>MOLASSES</b>	E	E	E	E	E	E	E	E	D	D	D
<b>MINERAL OILS</b>	TE	TE	TD	TE	TE	TE	TE	TE	TD	TD	TD
<b>MINERAL SPIRITS</b>	D	D	C	D	D	D	D	D	C	C	C
<b>MOTOR OIL</b>	D	D	C	D	D	D	D	D	C	C	C
<b>M-PYROL</b>	A	A	A	B	B	A	A	A	A	A	A
<b>NAPHTHA ALIPHATIC</b>	E	D	B	E	E	E	E	E	C	C	C

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>NAPHTHA AROMATIC</b>	D	C	A	E	E	D	D	D	B	B	B
<b>NICKEL CHLORIDE</b>	TC	TC	TB	TD	TD	TC	TC	TC	TB	TB	TB
<b>NICKEL NITRATE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>NICKEL SULFATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>NITRIC ACID 5%</b>	E	D	C	E	E	E	E	E	D	D	D
<b>NITRIC ACID 30%</b>	C	C	B	C	C	C	C	C	C	C	C
<b>NITRIC ACID 60%</b>	A	A	A	A	A	A	A	A	A	A	A
<b>NITROBENZENE</b>	TC	TC	TB	TC	TC	TC	TC	TC	TB	TB	TB
<b>OIL SOUR CRUDE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>OIL SWEET CRUDE</b>	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
<b>OLEIC ACID</b>	D	C	B	D	D	D	D	D	B	B	B
<b>OLEUM</b>	B	B	A	C	C	B	B	B	A	A	A
<b>OXALIC ACID</b>	D	C	B	D	D	D	D	D	B	B	B
<b>PERCHLORIC ACID</b>	C	B	A	C	C	C	C	C	A	A	A
<b>PERCHLOROETHYLENE</b>	D	C	B	D	D	D	D	D	B	B	B
<b>PHENOL 5%</b>	C	B	A	C	C	C	C	C	A	A	A
<b>PHENOL 85%</b>	A	A	A	B	B	A	A	A	A	A	A
<b>PHOSPHORIC ACID 40%</b>	D	C	B	D	D	D	D	D	C	C	C
<b>PHOSPHORIC ACID 85%</b>	B	B	A	B	B	B	B	B	A	A	A
<b>PICRIC ACID 10%</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>POTASSIUM ACETATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>POTASSIUM BROMIDE</b>	E	D	D	E	E	E	E	E	D	D	D
<b>POTASSIUM CARBONATE</b>	E	D	D	E	E	E	E	E	D	D	D
<b>POTASSIUM CHLORIDE</b>	D	D	C	D	D	D	D	D	D	D	D

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>POTASSIUM HYDROXIDE 10%</b>	E	D	C	E	E	E	E	E	D	D	D
<b>POTASSIUM HYDROXIDE 50%</b>	D	C	B	E	E	D	D	D	C	C	C
<b>POTASSIUM IODIDE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>POTASSIUM NITRATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>POTASSIUM PERMANGANATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>POTASSIUM PERSULFATE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>POTASSIUM SULFATE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>PROPIONIC ACID</b>	C	B	A	C	C	C	C	C	A	A	A
<b>PROPYLENE GLYCOL</b>	E	D	D	E	E	E	E	E	D	D	D
<b>PYRIDINE</b>	A	A	A	A	A	A	A	A	A	A	A
<b>SALICYLIC ACID</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>SALT BRINE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>SILVER NITRATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>SKYDROL</b>	C	C	C	C	C	C	C	C	C	C	C
<b>SODIUM ACETATE</b>	E	D	D	E	E	E	E	E	D	D	D
<b>SODIUM BENZOATE</b>	E	D	D	E	E	E	E	E	D	D	D
<b>SODIUM BICARBONATE</b>	E	D	D	E	E	E	E	E	D	D	D
<b>SODIUM BISULFITE</b>	TE	TD	TD	TD	TD	TD	TD	TE	TD	TD	TD
<b>SODIUM BISULFATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>SODIUM CARBONATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>SODIUM CHLORATE 50%</b>	TD	TD	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>SODIUM CHLORIDE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>SODIUM CHLORITE</b>	D	C	B	D	D	D	D	D	B	B	B
<b>SODIUM CHROMATE</b>	D	C	B	D	D	D	D	D	B	B	B

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

# CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>SODIUM DICHROMATE</b>	D	C	B	E	E	D	D	D	B	B	B
<b>SODIUM FERROCYANIDE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>SODIUM FLUORIDE</b>	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
<b>SODIUM HYDROXIDE 10%</b>	E	E	C	E	E	E	E	E	D	D	D
<b>SODIUM HYDROXIDE 50%</b>	E	E	C	E	E	E	E	E	D	D	D
<b>SODIUM HYPOCHLORITE 3%</b>	D	D	A	D	D	D	D	D	B	B	B
<b>SODIUM HYPOCHLORITE 5-15%</b>	A	A	A	A	A	A	A	A	A	A	A
<b>SODIUM OXALATE</b>	E	E	D	E	E	E	E	E	D	D	D
<b>SODIUM PEROXIDE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>SODIUM PHOSPHATE 10%</b>	E	D	C	E	E	E	E	E	C	C	C
<b>SODIUM SILICATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>SODIUM SULFATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>SODIUM SULFIDE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>SODIUM SULFITE</b>	E	E	D	E	E	E	E	E	D	D	D
<b>SODIUM TARTRATE</b>	E	D	C	E	E	E	E	E	D	D	D
<b>SODIUM THIOSULFATE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>STEARIC ACID</b>	D	C	B	E	E	D	D	D	B	B	B
<b>STYRENE</b>	D	C	B	D	D	D	D	D	B	B	B
<b>SULFAMIC ACID 25%</b>	TC	TB	A	TD	TD	TC	TC	TC	A	A	A
<b>SULFURIC ACID 10%</b>	E	D	C	E	E	E	E	E	D	D	D
<b>SULFURIC ACID 30%</b>	D	C	C	D	D	D	D	D	C	C	C
<b>SULFURIC ACID 98%</b>	C	B	A	C	C	C	C	C	B	B	B
<b>TALL OIL</b>	E	D	C	E	E	E	E	E	C	C	C
<b>TARTARIC ACID</b>	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.

## CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS

	NP253	NP254	NP255	NP256	NP256M	NP257	NP258	NP259	NP928	NP928HV	NP929
<b>A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE</b>											
<b>TETROCHLOROETHANE</b>	D	C	B	D	D	D	D	D	B	B	B
<b>TETRAHYDROFURAN</b>	A	A	A	A	A	A	A	A	A	A	A
<b>THIONYL CHLORIDE</b>	A	A	A	A	A	A	A	A	A	A	A
<b>TOLUENE</b>	D	C	B	D	D	D	D	D	C	C	C
<b>TOLUENE SULFONIC ACID</b>	D	C	B	D	D	D	D	D	B	B	B
<b>TOLUIDENE</b>	D	C	B	E	E	D	D	D	B	B	B
<b>TRICHLOROACETIC ACID 20%</b>	B	B	A	B	B	B	B	B	A	A	A
<b>TRICHLOROETHANE</b>	C	C	C	D	D	C	C	C	C	C	C
<b>TRICHLOROETHYLENE</b>	TC	TC	TB	TD	TD	TC	TC	TC	TB	TB	TB
<b>TRICESYL PHOSPHATE</b>	TD	TD	TB	TD	TD	TD	TD	TD	TB	TB	TB
<b>TRISODIUM PHOSPHATE</b>	E	D	C	E	E	E	E	E	C	C	C
<b>TURPENTINE</b>	D	D	B	D	D	D	D	D	C	C	C
<b>UREA SOLUTIONS</b>	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
<b>WHITE LIQUOR (PAPER)</b>	TD	TC	TB	TE	TE	TD	TD	TD	TB	TB	TB
<b>XYLENE</b>	D	D	C	D	D	D	D	D	D	D	D
<b>ZINC CHLORATE</b>	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
<b>ZINC SULFATE</b>	E	D	C	E	E	E	E	E	D	D	D

This data is provided as a service of National Polymers, Inc. and is believed to be accurate. However, this information is neither recommendations by NPI nor product specifications. NPI reserves the right to change or modify data as necessary.