

NP343 TECHNICAL DATA (Concrete Quick Fix)

PRODUCT DESCRIPTION: NP343 patch kit consists of a two component polymer packaged with aggregate for patching and repairing concrete.

RECOMMENDED FOR: Industrial repairing of spalled concrete, holes, cracks and thresholds or uneven concrete slabs.

NOT RECOMMENDED FOR: Expansion Joints.

SOLIDS BY WEIGHT: Nearly 100% cured

VOLATILE ORGANIC CONTENT:

5.5 grams per liter cured

STANDARD COLORS:

Gray colored when mixed and cured. The gray color will not develop until the curing process takes place.

RECOMMENDED THICKNESS:

The NP343 polymer patch kit can be applied at variable thicknesses.

COVERAGE PER KIT:

Coverage is dependent on hole size or size of area to be repaired.

PACKAGING

*Small patch kit consisting of a ½ pint of part A, ½ pint part B and ½ gallon (approx. 6.2#) of blended sand – packaged in gallon pail.

*Large patch Kit consisting of 1 pint part A, 1 pint part B and 1 gallon (approx. 12.4#) of blended sand – packaged in a 2 gallon pail.

MIX RATIO: The liquid mix ratio is 1:1 by volume

SHELF LIFE: 1 year in unopened containers

SHORE D HARDNESS: 71

TENSILE STRENGTH: 4,500 psi

ELONGATION: 5-6%

IMPACT RESISTANCE: Excellent

ABRASION RESISTANCE: Excellent

COMPRESSIVE STRENGTH:

4,400 (as a slurry with aggregate sand)

BOND STRENGTH: 535 psi (concrete failure)

DOT CLASSIFICATION:

Part B "not regulated"

Part A "not regulated"

VISCOSITY: Less than 30cps typical

PRIMER: Self-Priming

TOPCOAT:

None required. However, many types of products can be used as coatings or overlays for the area that has been patched.

CURE SCHEDULE (70 Degrees F)

Pot Life (100 gram mass)	1-4 minutes
Recoat or Topcoat	1 hour
Light Foot Traffic	10-20 minutes
Full Cure (Heavy Traffic)	1 hour
Application Temperature: 20-90 degrees F. (lower temperatures will require additional cure time)	

LIMITATIONS:

Because of the quick cure time for this product, it is best to work with one small area at a time. Typical working time after the three components are mixed according to directions is about 1-3 minutes.

Color stability may be affected by environmental conditions such as UV light, high humidity or chemical exposure. Product is not UV color stable.

Product may discolor if exposed to certain types of light such as sodium vapor lighting.

Final cured product colors may vary from batch to batch and be influenced the by silica aggregate when used.

Substrate temperature must be 5° F above dew point.

All new concrete must be cured for at least 30 days prior to application.

When applying material in cold areas, make sure the surface is clean and dry. Also, it is best to keep the material and aggregate sand at normal room temperature before mixing or use..

See reverse side for application instructions.

Test data based on neat resin unless otherwise noted.

Physical properties are typical values and not specifications.

See reverse side for limitations of our liability and warranty.

MIXING AND APPLICATION INSTRUCTIONS: NP343 Concrete Quick Fix

PRODUCT STORAGE: Store product in an area so as to bring the material to normal room temperature before using. Continuous storage should be above 55⁰ F to prevent product crystallization.

SURFACE PREPARATION: All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate. For repair of spalled concrete, a stiff wire brush can be used to remove all loose concrete. After wire brushing the spalled area, remove all loose dust and debris with an industrial vacuum.

PRIMER: The material is self-priming.

PRODUCT MIXING: The product has a 1:1 liquid mix ratio by volume. Mix only an amount of material that can be used in 1-3 minutes. Mix the liquids (½ pint part A and ½ pint part B) for 15 seconds and immediately add in the ½ gallon blended aggregate and remix.

PRODUCT APPLICATION: Immediately after the three components are mixed, (Product has a very short pot life), place the material into the area to be repaired with a trowel or other suitable equipment. Finally, trowel the floor to smooth out the area and remove any excess material. Allow the material to cure for ten to twenty minutes before foot traffic. For heavy equipment such as fork trucks, allow the material to cure for a half hour to an hour before using area that has been patched.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

*We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.***

COPYRIGHT 2/19/15 NATIONAL POLYMERS INC.