

NP7175 TECHNICAL DATA (Water Based Epoxy Textured Non-Slip Coating)

PRODUCT DESCRIPTION:

NP7175 is a 74% solids medium duty non-slip coating for applications in slippery or wet areas to prevent slips and falls from pedestrian and light rolling equipment traffic. This product was developed for use in industrial environments and incorporates modified epoxy resins to provide toughness, good chemical resistance, wear, corrosion resistance and excellent slip resistance performance.

RECOMMENDED FOR: Recommended for skidproofing industrial areas or docks in pedestrian or light rolling equipment areas. Also ideal for use in institutional and recreational areas.

SOLIDS BY WEIGHT: 74% (+/- 1%)

SOLIDS BY VOLUME: 60% (+/-1%)

VOLATILE ORGANIC CONTENT: Less than 97 g/l

STANDARD COLORS: Medium gray and tile red

RECOMMENDED FILM THICKNESS: 18 mils (average)

COVERAGE PER GALLON:

Typical coverage is 90 square feet per gallon when applied with a phenolic core roller applicator.

PACKAGING INFORMATION

1 gallon kit (volume approximately 0.93 gallons) consisting of a gallon can part A (not full) and a quart can part B (not full)

MIX RATIO:

11.55 pounds part A to 1.20 pounds part B by weight

SHELF LIFE: 1 year in unopened containers when stored according to directions.

COEFFICIENT OF FRICTION: Excellent ASTM F609

FINISH CHARACTERISTICS:

Low gloss to a nearly flat finish

ABRASION RESISTANCE: Excellent

ADHESION: 380 psi using an elcometer (concrete failure, no delamination)

VISCOSITY:

Part A= 1,000,000 cps (typical)

Part B= 74 krebs (typical)

DOT CLASSIFICATION:

Part A "not regulated"

Part B "not regulated"

FLASH POINT: Greater than 200°F

PRIMER:

A primer is optional but recommended.

Recommend NP015 or NP144PM as low odor options.

TOPCOAT:

None normally required.

CURE SCHEDULE (70 Degrees F)

Pot Life (150 gram mass)	90 minutes
Theoretical Pot Life (1 Gal)	1 Hour
Tack Free (Dry to touch)	5-8 hours
Light Foot Traffic	24 hours
Full Cure (Heavy Traffic)	72 days
Application Temperature: 50-90 degrees F with relative humidity below 90%.	

CHEMICAL RESISTANCE

xylene	C
MEK	A
methanol	A
ethyl alcohol	C
skydrol	B
10% sodium hydroxide	E
50% sodium hydroxide	E
10% sulfuric acid	C
70% sulfuric acid	A
10% HC1 (aq)	C
5% acetic acid	B
Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.	

LIMITATIONS:

Color stability or gloss may be affected by environmental conditions, high humidity or chemical exposure. Exposure to certain types of lighting such as sodium vapor lights may discolor the product.

Colors may vary from batch to batch. Therefore, use only product from the same batch for an entire job.

This product is not UV color stable, but has good resistance to color change for an epoxy product.

Substrate temperature must be 5°F above dew point.

For best results, apply with a phenolic core roller applicator, rolling the material out in the same direction for the entire application.

All new concrete must be cured for at least 30 days prior to application.

Mix each component well before using. Because this material is high in viscosity, it should be mixed thoroughly once the part A and B are combined until uniform in color and consistency.

Applications placed too thick may exhibit hairline cracking due to shrinkage.

See reverse side for application instructions.

Physical properties are typical values and not specifications.

See reverse side for limitations of our liability and warranty.

MIXING AND APPLICATION INSTRUCTIONS: NP7175 Water Based Epoxy Textured Non-Slip Coating

PRODUCT STORAGE: Store product in an area so as to bring the material room temperature before using. Continuous storage should be between 60 and 90 degree F. Low temperatures or great temperature fluctuations may cause product crystallization.

SURFACE PREPARATION: The most suitable surface preparation would be a fine brush blast (shot blast) to remove all laitance and provide a suitable profile. All dirt, foreign contaminants, oil, and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating.

PRODUCT MIXING: This product has a mix ratio of 11.55 pounds part A to 1.20 pounds part B by weight for standard colors. Standard packages are in pre-measured kits and should be mixed as supplied. We recommend that the kits not be broken down unless suitable weighing equipment is available. Before the two components are mixed together, mix the part A and part B separately to insure they are uniform before they are combined. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. Continue mixing for another couple of minutes to insure a homogeneous mixture that is properly mixed. Make sure you scrape the bottom and sides of the pail thoroughly while mixing. This material has a high viscosity – mix well. Improper mixing may result in product failure.

PRIMING: This product is intended to be used over a suitable primer. It is advisable to select a primer color similar to the color of the topcoat skidproof to be used. This product can also be used over a non-primed cement substrate, but adequate testing should be employed to assure adhesion and suitability before the actual application.

PRODUCT APPLICATION: Make certain that the primer where the product is to be applied is clean, sound and free of all laitance, dirt, dust, oil, grease, water or foreign contaminants and sufficiently cured to accept topcoats. Apply the mixed skidproof coating by using a phenolic core roller so as to spread out the material in a uniform manner. It is equally important to roll the entire surface area in one direction to align the peaks and valleys generated from the phenolic core to insure a uniform look throughout the application area. Pour a ribbon on the surface approximately 6 inches wide. Pull material toward you with a moderate amount of pressure, but do not over-roll too many times or press down too heavily.

RECOAT OR TOPCOATING: Although this product can be topcoated, it will not be easy to perform a topcoat application due to the rough texture of the surface. Accordingly, this product was developed for use without a topcoat. Product has only moderate UV and color stability. UV stable aliphatic urethanes are compatible for use as a topcoat only when properly applied so as not to diminish the slip resistance. If you topcoat, make sure the skidproof coat has tacked off before recoating.

CLEANUP: Use water compatible solvents such as PM solvent.

FLOOR CLEANING: Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS: Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle. Dependent on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

*We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.***

COPYRIGHT 9/1/12 NATIONAL POLYMERS INC.