

URETHANE TOPCOATS

Copyright National Polymers, Inc.
11/2020



All of the topcoats listed below offer superior performance properties: excellent abrasion and chemical resistance, UV stability.



HIGH PERFORMANCE



WATER BASED



POLYASPARTIC

Product Features

356
Moisture
Cured

322
HPU - VOC
Compliant

359
High
Wear

520
WB Low
Gloss

521
WB
Gloss

344
Quick
Cure

449
Lowest
VOC

449SF
Most
Working
Time

444X
Easy 1:1
Low Odor

PACKAGING

1 Gal
5 Gal

1.5 Gal Kit
3 Gal Kit
15 Gal Kit

1 Gal Kit
4 Gal Kit

1.5 Gal Kit
3 Gal Kit
15 Gal Kit

1.5 Gal Kit
3 Gal Kit
15 Gal Kit

1.5 Gal Kit
3 Gal Kit
15 Gal Kit

1.25 Gal Kit
2.5 Gal Kit
25 Gal Kit

1.25 Gal Kit
2.5 Gal Kit
25 Gal Kit

2 Gal Kit
10 Gal Kit

FINISH

HIGH
GLOSS

HIGH
GLOSS

*Satin version
available (322S)

CLEAR
COLORS

SEMI
GLOSS

CLEAR
PIGMENTS
Pigment packs sold
separately

LOW
GLOSS

CLEAR

HIGH
GLOSS

CLEAR
PIGMENTS
Pigment packs sold
separately

GLOSS

CLEAR
PIGMENTS
Pigment packs sold
separately

GLOSS

CLEAR
PIGMENTS
Pigment packs sold
separately

GLOSS

CLEAR
PIGMENTS
Pigment packs sold
separately

GLOSS

CLEAR
PIGMENTS
Pigment packs sold
separately

CLEAR OR COLORS

CLEAR

CLEAR
COLORS

CLEAR
PIGMENTS
Pigment packs sold
separately

CLEAR

CLEAR
PIGMENTS
Pigment packs sold
separately

CLEAR
PIGMENTS
Pigment packs sold
separately

CLEAR
PIGMENTS
Pigment packs sold
separately

CLEAR
PIGMENTS
Pigment packs sold
separately

CLEAR
PIGMENTS
Pigment packs sold
separately

MIXING

1 Part

2A:1B

3 Part

*Premeasured kits, see
data sheet for details

2A:1B

2A:1B

2A:1B

3A:2B

3A:2B

1A:1B

VOC (g/L)

329

335

95

< 50

306

159

50

100

95

% SOLIDS (BY WEIGHT)

65%

73%
Clear: 64%

93%

60%

42%

85%

95%

90%

84%

READY FOR LIGHT TRAFFIC*

14-24 hrs

14-24 hrs

14-24 hrs

24 hrs

24 hrs

3-5 hrs

3-5 hrs

6-8 hrs

24 hrs

WORKING TIME

3-5 hrs

2-4 hrs

1-2 hrs

1 hr

1 hr

5-10 min

10-15 min

20-25 min

10-20 min

COVERAGE (SQ.FT. PER GAL)

320-500
3-5 mils

*mils (wet thickness)

320-500
3-5 mils

600

320-500
3-5 mils

320-500
3-5 mils

133-320
5-12 mils

133-200
8-12 mils

133-267
6-12 mils

133-320
5-12 mils

*Cure times based on 70 Degrees F Application Temperature

PHONE: 800.831.5600
www.nationalpolymers.com