

NP359 TECHNICAL DATA (High Solids High Wear Urethane)

PRODUCT DESCRIPTION:

NP359 is a three component aliphatic urethane floor finish that exhibits excellent characteristics for abrasion resistance, chemical resistance, flexibility, weathering and UV stability.

RECOMMENDED FOR: Recommended for auto service centers, warehouses, computer rooms, laboratories, aircraft hangers, cafeterias, and some chemical exposure areas.

SOLIDS BY WEIGHT and VOLUME: Mixed= 93% solids by weight / 92% solids by volume (+,-2%)

VOLATILE ORGANIC CONTENT: Less than 95 grams per liter (for colors or clear mixed)

STANDARD COLORS: Opaque clear/amber clear with color options using our urethane color packs. The colorants may be added at the ratio of 1 pint per gallon kit of the NP359 product. However, the colorants may not impart a total hide over dissimilar colored basecoats and therefore, a basecoat must be applied in the same color before applying this product. Color packs available for this product line are white, off white, light gray, medium gray, charcoal gray, tile red, tan, light blue and blue. The clear is not suitable as a topcoat over colored systems.

COVERAGE PER GALLON Kit (colors): 600 square feet per gallon (a gallon kit + pigment = approximately 1.1 gallons and yields 660 square feet actual coverage per colored kit.

COVERAGE PER GALLON KIT (clear): 600 square feet per gallon kit

PACKAGING INFORMATION: 1 gallon kits (1 pint part A) with (0.70 gallons part B) and (3.0# part C.) (weights and volumes approximate) (approximately 1 gallon)

MIX RATIO: 1.08# part A with 6.45# part B and 3.0# part C (weights approximate)

FINISH CHARACTERISTICS: Semi-gloss/eggshell (typical gloss is 20-40 @ 60 degrees)

SHELF LIFE: 6 months in unopened containers.

ABRASION RESISTANCE: Taber abrasor CS-17 calibrase wheel with 1000 gram total load and 500 cycles = 15-20 mg loss

IMPACT RESISTANCE: Gardner Impact = 160 in. lb. (passed)

FLEXIBILITY: No cracks on a 1/8" mandrel

ADHESION: On a properly prepared epoxy basecoat, the adhesion should exceed 300 psi @ elcometer (concrete failure, no delamination)

VISCOSITY: Mixed liquids A/B = 1000-2000 cps (typical)

DOT CLASSIFICATIONS: Part A "NA1993, COMBUSTIBLE LIQUID N.O.S., 3, PG III" Part B "ENVIRONMENTALLY HAZARDOUS SUBSTANCES, LIQUID, N.O.S., UN3082, 9, PGIII,"

PRIMER: Apply a suitable basecoat. For thin mil systems, we recommend NP015 in clear for clear NP359 or in a color that matches the color pack for the NP359 when colored. For a high build color system, we recommend NP707 in a matching color for the intermediate coat.

TOPCOAT: We do not recommend multiple coats of this product or other topcoats.

CURE SCHEDULE (70 Degrees F)

Pot Life 1 Gal Vol. (Max time to apply)	1-2 hours
Tack Free (Dry to Touch)	3-6 hours
Recoat or Topcoat	6-10 hrs
Light Foot Traffic	14-24 hrs
Full Cure (Heavy Traffic)	3-5 days
Application Temperature: 50-90 degrees F with relative humidity between 50% and 90%	

CHEMICAL RESISTANCE

Acetic Acid 5%	C
MEK	B
Gasoline	D
50% Sodium Hydroxide	D
10% Sulfuric	D
10% Hydrochloric Acid	D
20% Nitric Acid	C
Ethylene Glycol	D
Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.	

LIMITATIONS:

Color or gloss may be affected by humidity, temperatures, chemical exposure, application thickness, exposure to lighting such as sodium vapor lights. For best results use a high quality 3/8" nap roller.

Slab on grade requires moisture barrier

Substrate temperature must be 5°F above dew point

All new concrete must be cured for at least 30 days

Physical properties are typical values and not specifications

Tire contact may cause staining and discoloration

Colors may vary from batch to batch, therefore, use only product from the same batches for an entire job.

See reverse side for application instructions.

See reverse side for limitations of our liability and warranty.

Do not use if relative humidity is below 25%

Material has to be applied at the recommended thickness per gallon uniformly for proper appearance and development of physical properties.

The epoxy basecoat must be abraded/de-glossed for proper adhesion.

MIXING AND APPLICATION INSTRUCTIONS: NP359 High Solids High Wear Urethane

PRODUCT STORAGE: Store product at normal room temperature before using. Storage should be between 60 and 90 degree F.

SURFACE PREPARATION: Surface preparation will vary according to the type of complete system to be applied. For a one or two coat thin build system over concrete, (3-10 mils dry) we recommend either mechanical scarification or acid etching until a suitable profile is achieved. For a complete system build higher than 10 mils dry, we recommend a fine brush blast (shot blast). All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4' X 4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding. It is crucial that the epoxy basecoat is thoroughly sanded until the surface is de-glossed and appropriately and thoroughly scratched. It is recommended that a minimum 80 grit paper be used.

PRODUCT MIXING: This product has three components. The part A should be mixed with the part B thoroughly and then the part C should be added and mixed in well to insure a uniform mixture. The kits come prepackaged and should be used in their entirety and should not be broken down. If a color pack is used, it is recommended that the color pack be combined with the part A and part B prior to adding the part C aggregate and then mixed well. After the three (or four, if color packs are used) parts are combined, mix extremely well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. Avoid whipping air into the coating. Improper mixing may result in product failure. Once the material is opened, it cannot be re-sealed for later use.

PRODUCT APPLICATION: Pour the mixed material into the application tray. Apply at the rate of 600 square feet per gallon in a uniform manner with a 3/8" nap roller. For uniform appearance, it is critical that the material is not applied thicker than this application rate. Dip the roller in the coating and roll out excess material in the roller tray prior to the actual application to the substrate. Overlap subsequent passes being sure no excess material is applied when overlapping. Make sure the floor has just enough material to cover evenly in a thin application. Finally, re-roll the area in the opposite direction of the first pass applications to level and even the application. The final re-rolling for the entire floor should be in the same direction. Remix the material in the application tray to maintain a uniform mix throughout the application process. If the appearance is not satisfactory, re-roll until the area is uniform in appearance. It is almost impossible to over-roll this material. The last step in the application process (wearing spiked shoes) is to pull the roller tool across the entire slab in one direction without applying any pressure and repeating this process by overlapping until the entire slab has been re-rolled. This will help blend in any roller and overlap marks. Maintain temperatures and humidity within the recommended ranges during the application and during the curing process. Make sure the substrate has a suitable epoxy primer that has been de-glossed (see surface preparation above) It is best to maintain a wet edge to avoid roller marks. Direct sunlight or high temperatures may cause visible roller marking during application. Too thick of an application may result in solvent entrapment and product failure. The Surface must be dry before the application of this product.

RECOAT OR TOPCOATING: Multiple coats of this product are not recommended without thoroughly evaluating the adhesion in conjunction with a thorough deglossing. If you opt to apply multiple coats of this product, a test area must be applied to test adhesion before attempting to apply multiple coats over the entire job. If you opt to recoat this product, you must first be sure that all of the solvents have evaporated from the coating during the curing process and properly de-gloss and roughen the surface (see surface preparation above). The information on the front side are reliable guidelines to follow. However, it is best to test the coating before recoating or topcoating. This can be done by pressing on the coating with your thumb to verify that no fingerprint impression is left. Always remember that colder temperatures will require more cure time for the product. Before recoating or topcoating, check the coating to insure no contaminants exist. If contaminants are present on a previous coat, remove with a standard detergent cleaner and allow to thoroughly dry. Although not recommended, when recoating this product with subsequent coats, it is advisable to apply the recoat before 24-48 hours pass only after proper surface preparation and adhesion testing has been completed.

CLEANUP: Use ketone solvents or other suitable cleaning solvent

FLOOR CLEANING: Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS: Restrict the use of the floor to light traffic, non-harsh chemicals and water until the coating is fully cured.. Dependent on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

*We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.***

COPYRIGHT 2/15/15 NATIONAL POLYMERS INC.